

PRODUCT INFORMATION

CYROLITE® MD zk6

Product Profile:

CYROLITE® MD zk6 acrylic polymer is an amorphous, impact modified thermoplastic injection molding and extrusion compound based on polymethyl methacrylate (PMMA) for the medical industry.

Typical properties of CYROLITE® MD zk6 acrylic polymers are:

- High light transmission with little haze
- 3 times the impact resistance of unmodified acrylics
- Excellent dimensional stability
- Excellent bonding to PVC tubing
- Can be thermal bonded, ultrasonic and laser welded
- Improved tensile elongation

The special Properties of CYROLITE® MD zk6 polymer are:

- High impact/ break resistance and strength
- Medium heat resistance
- Lower melt flow rate applications

Application:

Used for injection molding of medical devices and diagnostics industries.

Examples:

Cassettes, Test Packs, Filter Housings, Lenses, Microfluidics, Guard Clips, Luers, Luer Locks, Tube Connectors, IV Catheter Hubs, Y Sites.

Processing:

CYROLITE® MD zk6 polymer can be processed in injection molding machines and extrusion lines with 3-zone general purpose screws.

Physical Form / Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Regulatory and compliance requirements:

Meets requirements of the United States Pharmacopeia Class VI; ISO 10993-1 in FDA for food contact for all use conditions up to and including hot filled or pasteurized above 150 degrees F (e.g., Condition 21 CFR 176.170) for all food types except those containing more than 8% alcohol.

Properties:

	Parameter	Unit	ASTM-Standard	CYROLITE® MD zk6 Typical Value
Mechanical Properties				
Tensile Strength		psi [MPa]	D 638	6300 [43.4]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.22 [1.5]
Tensile Elongation @ Yield		%	D 638	5
Tensile Elongation @ Break		%	D 638	55
Flexural Strength		psi [MPa]	D 790	8600 [59.3]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.22 [1.5]
Notched Izod	¼" bar @ 23°C	ft-lb/in [J/m]	D 256	1.1 [58.1]
Notched Izod	¼" bar @ 0°C	ft-lb/in [J/m]	D 256	0.70 [36.8]
Rockwell Hardness		M Scale	D 785	40
Thermal Properties				
Vicat Softening Point	264 psi	°F [°C]	D 1525	201 [94]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	194 [90]
Coeff. of Linear Therm. Expansion	32 - 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	mm/mm/°C	D 696	0.000072
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	1.7
Optical Properties				
	d = 3.2 mm			
Light Transmission		%	D 1003	91.5
Haze		%	D 1003	1
Yellowness Index			E 313	0.3
Other Properties				
Specific Gravity			D 792	1.16
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.004 - 0.007
Bulk Density		g/cc	D 1895	0.71

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer.

Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Roehm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2022 Roehm America LLC. All rights reserved.

Roehm America LLC • 8 Campus Drive • Suite 450 • Parsippany, NJ 07054 • USA
www.cyrolite.com
www.roehm.com

RÖHM